HIGH STRENGTH ACRYLIC PBR PANEL With Condensation Abatement Under-Panel

STANDARD CONFIGURATION


F&F ASSEMBLIES insulated light transmitting assembly consists of a full 8 oz. ACRYLIT light transmitting panel with a 5 oz. clear light transmitting panel laminated onto it utilizing a series of thermal breaks with compartmentalization to afford minimal loss of thermal conductivity in the event of penetration of hail etc..

The F&F ASSEMBLIES Insulated System furnishes a "U" Factor of .61, which is a tested factor with test data included for the ACRYLIT SYSTEM.

The system is designed with fastener locations at both ends of the panel as well as the center section to allow for fastening across the center purlin and lap locations.




BOTTOM VIEW



All dimensional variations of this system are subject to change at the discretion of the customer's engineering requirements.

10' - 8" Standard Dimensions



11' - 0" Standard Dimensions

		58.50in	132.00in	58.56in		\exists
F						
F						
2.5	5.00in		5.00in		. [2.50in
						=



TECHNICAL DATA SHEET

GLASTEEL Acrylit_{GC} HIGH STRENGTH FIBERGLASS PANELS

Product Description: Consisting of an 8 oz. 100% Acrylic Translucent panel Woven Roving Strand combined with chopped strand Fiberglass Reinforcement PHYSICAL PROPERTIES

	I III GIGAL I NOI ENTILO			
Property	ASTM STD.	Typical Values		
TENSILE STRENGTH	D-638	25,772 psi.		
TENSILE MODULUS	D-638	1.52 X10 ⁶ psi		
FLEXURAL STRENGTH	D-790	24,306 psi.		
FLEXURAL STRENGTH	D-790	0.79 X10 ⁶ psi.		
COMPRESSIVE STRENGTH	D-695	28905 psi.		
SELF-IGNITION TEMPERATURE	D-1929	GREATER THAN 650° F.		
SMOKE DENSITY	E-84	<450		
COMPRESSIVE MODULUS	D-695	105 x 10 ⁶ psi		
BURNING RATE	D-635	<2.5 in / min.		
UNIFORM BUILDING CODE				
CLASSIFICATION	D-635	CC2		
BARCOL HARDNESS	D-2583	40-50		
LIGHT TRANSMISSION	D-1494	55-60		
U FACTOR/ SINGLE SHEET	NFRC 102-2004	1.08 BTU / Hr ft ² F		
U FACTOR/ DOUBLE SHEET	NFRC 102-2004	.61 BTU / Hr ft ² F		
(18oz & 15oz Fiberglass Panel)	NFRC 102-2004	.01 B10 / HI IL F		
R FACTOR/ SINGLE SHEET	Calculated	0.92592593		
R FACTOR/ DOUBLE SHEET	Calculated	1.6393443		
(18oz & 15oz Fiberglass Panel)	Calculated			
LINEAR THERMAL EXPANSION	D-638	1.9 X 10 ⁻⁵ in./in./ ⁰ F		
BEARING STRENGTH	D-953	24.8 ksi (3.889		
WATER ABSORBTION	D-570	0.25% @72 ⁰ F / 72hrs.		
SOLAR HEAT GAIN/ SINGLE SHEET	NFRC 201-2004	0.45		
SOLAR HEAT GAIN / DOUBLE SHEET	NFRC 201-2004	0.35		
(18oz & 15oz Fiberglass Panel)	NFNC 201-2004	0.33		
SOLAR ABSORBANCE	E-903	77.73		
REFLECTANCE AND EMMITANCE	E-1371 / E-1918	.58 / .91		
IZOD IMPACT	D-4812	18.59 Ft-lb / in ²		
LUMINEOUS TRANSMITTANCE / SINGLE SHEET	D1003-07	77.18%		
LUMINEOUS TRANSMITTANCE / DOUBLE SHEET (1 8oz & 1 5oz Fiberglass Panel)	D1003-07	60% Calculated		
HAZE	D1003-07	112.78%		

Tolerances:

PANEL WEIGHT	+/- 10%
RIB HEIGHT	+/- 1/16th
LENGTH	+/- 1/8th
WIDTH	+/- 1/8th
SOUARENESS	• •

Codes and Approvals:

ASTM D-3841 SPECIFICATIONS FOR GLASS FIBER-REINFORCED POLYMERS

Plastic Panels "UL90" Recognized Component File (#R5214)

TEXAS WINDSTORM RWA-03 (PDF)

FLORIDA APPROVAL (Roof FL-15531) (WALL FL 5614-R)

The information offered hereinis offered without charge and is accepted at receipients sole risk. Because conditions of use vary and are beyond our knowledge and control, Glasteelmakes norepresentation about and is not responsible for the accuracy of data, nor with toxicological effect or industrial hygiene requirements associated with particularuses of any productor process described herein. Glasteel requests that customers test and inspect our products before use and satisfy thenmselves as to contents and suitability. Nothing herein shall constitute a warranty, express or implied, including any warranty or merchantability or fitness, noris protection from any law or patent inferred. Allpatent rights are reserved. The exclusie remedy for all proven claims is replacement of Glassteel materials only.